

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 195 142
A1

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 85301855.4

(51) Int. Cl.⁴: C 25 C 3/20

(22) Date of filing: 18.03.85

(43) Date of publication of application:
24.09.86 Bulletin 86/39

(84) Designated Contracting States:
DE FR

(71) Applicant: **ALCAN INTERNATIONAL LIMITED**
1188 Sherbrooke Street West
Montreal Quebec H3A 3G2(CA)

(72) Inventor: **Desclaux, Paul**
1685, Castner
Jonquiere Quebec, G7S 3A5(CA)

(72) Inventor: **Huni, Jean-Paul Robert**
3052, Dickie Street
Jonquiere Quebec, G7S 2L4(CA)

(74) Representative: **Pennant, Pyers et al,**
Stevens, Hewlett & Perkins 5 Quality Court Chancery
Lane
London, WC2A 1HZ(GB)

(64) Controlling **ALF 3** addition to al reduction cell electrolyte.

(57) A method for controlling the rate of aluminium fluoride addition to a cryolite-based electrolyte of an aluminium electrolytic reduction cell makes use of the known ration between cell temperature and bath (NaF:A1F₃) ratio. A target temperature is established corresponding to a target bath ratio. The cell temperature is measured at intervals and the rate of A1F₃ addition altered depending on whether the measured temperature is above or below the target temperature. The method is faster than traditional methods involving analysis of electrolyte samples, and is amendable to computer control.

EP 0 195 142 A1

- 1 -

Controlling AlF_3 Addition
to Al Reduction Cell Electrolyte

The process of Hall and Heroult for the production of aluminium by the electrolytic reduction of alumina (Al_2O_3) involves the use of an electrolyte based on molten cryolite (Na_3AlF_6). The electrolyte contains an addition of 5 to 7% of aluminium fluoride (AlF_3), which lowers the melting point so as to permit operation in the range 950 to 1000°C, and lowers the content of reduced species in the electrolyte and thereby improves current efficiency. Losses of AlF_3 during operation of the cell are made good by addition of fresh AlF_3 to the electrolyte; for example, the AlF_3 requirement for a 275 KA cell may be around 60 Kg per day. Generally, a target ratio of $\text{NaF}:\text{AlF}_3$ is established for a cell, which may be for example around 1.10 by weight, and AlF_3 additions adjusted with reference to this ratio.

In conventional operation, samples of electrolyte are periodically withdrawn and analysed for bath ratio by determination of their chemical composition. The AlF_3 requirements of the electrolyte are deduced from the bias between the actual value of the bath ratio and the target value. This method has the disadvantage of requiring time for sampling and analysis (even though modern techniques such as X-ray diffraction may be used). Sample identities need to be carefully preserved to avoid mistakes. It is an object of the present invention to provide a method of controlling AlF_3 additions to the electrolyte, which is simpler and quicker and is amenable to computerized operation.

It is well known that, under steady state

operation of a cell, there is a relationship between bath ratio and electrolyte temperature, which is substantially linear within the normal operating range specifically, as the bath ratio rises, (e.g. as a result of removal of AlF_3 from the system) the electrolyte temperature also rises. This relationship holds good over a range of about 10°C greater or less than the target operating temperature of the cell, and it is with this fairly narrow range that the present invention is concerned. It may be noted that there are inevitably fluctuations of electrolyte temperature arising, for example, from changes in the anode-cathode distance or the Al_2O_3 concentration, but these are essentially short-term changes, continuing for minutes or at most a few hours. Since changes in bath ratio are measured over periods of at least several hours, these short-term changes can generally be ignored.

This invention makes use of the known dependence of electrolyte temperature on bath ratio to control the rate of addition of AlF_3 to the electrolyte. Thus in a broad sense, the invention provides a method of controlling the addition of AlF_3 to a cryolite-based electrolyte of an aluminium electrolytic reduction cell, which method comprises:-

- a) establishing a target cell temperature (T_t),
- b) establishing a standard rate of addition of AlF_3 ,
- c) measuring the actual cell temperature (T),
- d) in response to the actual temperature measurement c) altering the rate of addition of AlF_3 ,
increasing the rate if T is greater than T_t , and
decreasing the rate if T is less than T_t , and
- e) repeating steps c) and d) at intervals.

Establishing a target cell temperature is tantamount to establishing a target bath ratio, and can be done by conventional means. If desired, the method of this invention can be enlarged to alter the target cell

temperature from time to time in the light of changing conditions. However, it is usually found that the target cell temperature remains constant during the life of the cell.

5 To establish a standard rate of addition of AlF_3 , it is merely necessary to determine approximately the average AlF_3 requirements of the cell over a period of time. This standard rate may change with time.

10 Cell temperature may be measured in a variety of ways and at a variety of locations. It is possible to measure the electrolyte temperature directly; but, as noted above, this may not always be satisfactory due to short-term fluctuations in electrolyte temperature. Alternatively, cell temperature can be measured by
15 means inserted in the side wall, or the floor, or in a cathode current collector in the cell floor. In cells with conventional carbon floors, horizontal steel bars are used to recover the current, and thermocouples can conveniently be positioned at intervals along a
20 longitudinal hole in one of these. Temperature measurements effected within the wall or floor of the cell have the advantage that they should not be affected by short term fluctuations.

25 AlF_3 additions are generally made in batches at suitable intervals of time. Altering the rate of addition of AlF_3 may involve altering the size of the batches or the intervals between additions, or both. For example, the rate of AlF_3 addition may be doubled if the actual temperature is above the target temperature,
30 or halved if the actual temperature is below the target temperature. This altered rate of addition may be continued for a specified time or until the next temperature measurement is effected. It should not be necessary to measure the actual cell temperature more
35 than once every few hours, and indeed a measurement once every twenty-four hours generally provides a

perfectly satisfactory level of control.

A preferred embodiment of the method of the invention comprises the following steps:-

1. Establishing a target operating temperature for the cell, which depends on the target bath ratio.
2. Establishing a standard AlF_3 addition rate which corresponds with the needs of a cell running in a stable condition at the target temperature.
3. Measuring the actual cell temperature on a regular basis, e.g. every twenty-four hours.
4. Determining a first correction based on the difference between the actual measured temperature and the target temperature.
5. Determining a second correction based on the difference between the actual measured temperature and the preceding measured temperature.
6. Applying the first and second corrections to the standard AlF_3 addition rate to define a corrected AlF_3 addition rate.
7. Making AlF_3 additions to the electrolyte at that corrected rate within a given period of time after making the temperature measurement.

The method of the invention can easily be applied to computer control of cell operation by applying the following formula:-

$$A_{n+1} = K_1 (T_t - T_n) + K_2 (T_n - T_{n-1}) + A_s$$

Where

- 30 A_{n+1} is the corrected AlF_3 addition to be made during period $n + 1$.
- A_s is the standard AlF_3 addition corresponding to the needs of the cell when stable at the target temperature.
- 35 T_t is target electrolyte temperature of the

operating cell.

T_n is actual measured electrolyte temperature at the point of time n .

5 T_{n-1} is the actual temperature obtained by the preceding measurement at commencement of period $n-1$.

K_1 is a constant which is applied to the difference between T_t and T_n to obtain a first required correction.

10 K_2 is a constant which is applied to the difference between T_n and T_{n-1} to obtain a second required correction.

K_1 and K_2 are functions of cell size and amperage and desired speed of response. They may be established by a statistical analysis of the relationship between change in electrolyte temperature and AlF_3 requirements. However, if K_1 and K_2 are chosen such that the speed of response is too rapid, then there is a danger of over-control. K_1 should generally be larger than, and opposite in sign to, K_2 . In practice, the value of K_1 is found to vary in approximate linear relationship with the volume of molten cell electrolyte.

Example

25 In a 275KA cell, the following values were determined by experiment.

$T_t = 955^\circ C$, this corresponding to a desired bath ratio of 1.10.

$A_s = 60 Kg/24h$.

$K_1 = -5 Kg/^\circ C.day$.

30 $K_2 = 2 Kg/^\circ C.day$.

During an eleven day period the cell electrolyte was sampled for bath ratio determination once every 24h., electrolyte temperature being measured at the time of sampling. The following table shows the AlF_3 additions required according to the above mentioned formula.

5

10

15

Electrolyte Temperature °C	Bath Ratio	AlF ₃ Addition Kg/24h.
947	1.09	28
949	1.04	34
949	1.10	30
948	1.07	23
952	1.10	53
951	1.05	38
952	1.11	47
960	1.06	101
947	1.07	nil*
948	1.09	27
947	1.05	18

*Formula gave negative value

20

At no time during this period did the bath ratio deviate from the target by more than 0.05.

C L A I M S

1. A method of controlling the addition of AlF_3 to a cryolite-based electrolyte of an aluminium electrolytic reduction cell, which method comprises:-

- a) establishing a target cell temperature (T_t),
- b) establishing a standard rate of addition of AlF_3 ,
- c) measuring the actual cell temperature (T),
- d) in response to the actual temperature measurement
c) altering the rate of addition of AlF_3 ,
increasing the rate if T is greater than T_t , and
decreasing the rate if T is less than T_t , and
- e) repeating steps c) and d) at intervals.

2. A method of controlling the addition of AlF_3 to a cryolite-based electrolyte of an aluminium electrolytic reduction cell, which method comprises the following steps:-

1. Establishing a target operating temperature for the cell, which depends on the target bath ratio.
2. Establishing a standard AlF_3 addition rate which corresponds with the needs of a cell running in a stable condition at the target temperature.
3. Measuring the actual cell temperature on a regular basis.
4. Determining a first correction based on the difference between the actual measured temperature and the target temperature.
5. Determining a second correction based on the difference between the actual measured temperature and the preceding measured temperature.
6. Applying the first and second corrections to the standard AlF_3 addition rate to define a corrected AlF_3 addition rate.

7. Making AlF_3 additions to the electrolyte at that corrected rate within a given period of time after making the temperature measurement.
3. A method as claimed in claim 2, wherein step 6 is performed by means of the following formula:-

$$A_{n+1} = K_1 (T_t - T_n) + K_2 (T_n - T_{n-1}) + A_s$$

where

- A_{n+1} is the corrected AlF_3 addition to be made during period $n + 1$.
- A_s is the standard AlF_3 addition corresponding to the needs of the cell when stable at the target temperature.
- T_t is target electrolyte temperature of the operating cell.
- T_n is actual measured electrolyte temperature at the point of time n
- T_{n-1} is the actual temperature obtained by the preceding measurement at commencement of period $n-1$.
- K_1 is a constant which is applied to the difference between T_t and T_n to obtain a first required correction.
- K_2 is a constant which is applied to the difference between T_n and T_{n-1} to obtain a second required correction.
4. A method as claimed in claim 3, wherein K_1 and K_2 are established by statistical analysis of the relationship between change in electrolyte temperature and AlF_3 requirements.
5. A method as claimed in any one of claims 1 to 4, wherein control of the cell is performed by a computer.



European Patent
Office

EUROPEAN SEARCH REPORT

0195142
Application number

EP 85 30 1855

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	CHEMICAL ABSTRACTS, vol. 95, no. 11, November 1981, page 503, no. 194439e, Columbus, Ohio, US; & SU - A - 852 975 (ALL-UNION SCIENTIFIC-RESEARCH AND DESIGN INSTITUTE OF THE ALUMINUM, MAGNESIUM, AND ELECTRODE INDUSTRY) 07-08-1981 * Whole abstract *	1	C 25 C 3/20
A	CH-A- 262 339 (FERRAND) * Page 1, lines 17-32; page 1, lines 41-61; page 6, lines 49-74; page 7, lines 50-57 *	1	
A	EP-A-0 044 794 (ALUMINIUM PECHINEY) * Page 3, lines 35-39; page 4, lines 1-10; page 4, lines 21-30; page 11, lines 27-30 *	1, 2, 4	TECHNICAL FIELDS SEARCHED (Int. Cl.4)
A	DE-A-1 926 099 (KAISER ALUMINIUM & CHEMICAL CORP.) * Claim 1; page 13, lines 9-16; page 14, lines 10-21 *	1, 4	C 25 C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18-11-1985	Examiner COOK S.D.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	